



## PRIMA

Property	Standard	Unit	Result
----------	----------	------	--------

### DESCRIPTION

Surface	X PUR scuff-resistant surface		
Backing	Combined closed cell foam system		
Thickness	EN ISO 24346	mm	4,5
Top layer	EN ISO 24340	mm	0,9
Weight	EN ISO 23997	g/m <sup>2</sup>	2800
Width	EN ISO 24341	m	2
Standard roll length	EN ISO 24341	m	20 ± 10%

### CLASSIFICATION

Product specification	Vinyl indoor sports floor. Meets the requirements of EN 14904 on sub-constructions		
Impact sound insulation	EN ISO717-2	dB	21
Thermal resistance	-	m <sup>2</sup> K/W	0,04
Reaction to fire	EN 13501	-	C <sub>fl</sub> -s1
Formaldehyde emission	-	-	No formaldehyde
Pentachlorophenol	-	-	No pentachlorophenol

### SPORT PROPERTIES

Friction	EN 13036-4	-	80-110
Shock absorption	EN 14808	%	20
Vertical deformation	EN 14809	mm	0,7
Ball rebound	EN 12235	%	98
Specular gloss	EN 2813	%	< 30

### TECHNICAL CHARACTERISTICS

Dimensional stability	EN ISO 23999	%	± 0,2
Indentation resistance	EN 1516	mm	<0,5
Resistance to rolling load	EN 1569	N	1500
Colour fastness	ISO 105 B02	-	6
Chemical resistance	EN ISO 26987	-	no change
Abrasion resistance	EN ISO 5470-1	mg/1000cycles	< 250


### OTHERS




3338



6170



7483



2519

Limited warranty



Antimicrobial treatment



No periodic renewal needed; Solvent and heavy metal free

Cleanability



Environmental attributes



**GRABOPLAST Floor Covering Manufacturers Ltd.**

H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100  
mail@graboplast.hu www.graboplast.hu